



TDS 075  
Issue 4  
08/05/15

# CDR 1111

## Passivating - Decontamination. Austenitic Stainless Steels.

**CDR 1111** is formulated to remove the metallic contaminations and restore the passive layer on austenitic stainless steel surface.

### CHARACTERISTICS:

Form: acid white paste  
Density at 20°C : 1,70  
pH < 1  
Flammable: no

### PACKAGING:

**CDR 1111** is supplied in card box containing 4 x 2 kg or 4 x 7,5 kg polyethylene drums / container, UN-approved for hazardous goods.

**CDR 1111** must be preserved at the shelter of freezing.

Exposure to high temperatures, such as in direct sunshine, should be avoided, as this may damage the gel / paste.

The products are perishable and should not be kept in storage longer than necessary. They have a maximum shelf life of one year when stored at room temperature.

### SAFETY LEGISLATION:

Users should wear acid resistant overall, gloves and rubber boots. Goggles or face visor should be used and, if necessary, suitable respiratory protective devices.

The waste water produced by rinsing contains acids and should be treated with **Neutril C**.

The neutralisation agent also precipitates heavy metals, and the resultant should be sent for deposition according to the local regulations.

Use in a ventilated room.

When in contact with other metals (carbon steels), **CDR 1111** releases red nitrous fumes which can't be inhaled.

ASK FOR AND CONSULT THE MATERIAL SAFETY DATA SHEET

### USAGE:

**CDR 1111** is ready for employment.

The paste is recommended for the brush passivation of weld seams and smaller surfaces.

Results can be reached after one or several applications lasting from 30 minutes to 1 hour.

Rinse with high pressure water or with a sponge. The best results are achieved by using a high pressure water jet.