

Fluidox ECR

FT 344 Issue 5 15/01/2010

Pickling spray.
Austenitic Stainless Steel.

FLUIDOX ECR has been designed in order to remove welding and heat micro-slag as well as undesired metallic residues, generally without prior degreasing.

FLUIDOX ECR is specially adapted for large surfaces.

Contain a pickling indicator. Red colour is turning to pale green when pickling is uniform.

CHARACTERISTICS:

Red, viscous, acid liquid
Density at 20 °C : $1,20 \pm 0,02$
pH < 1
Non flammable
1 kg treats $\approx 3 \text{ m}^2$

PACKING:

Non returnable plastic containers of 20 & 30 kg
Keep away from frost

SAFETY LEGISLATION:

Corrosive and toxic product
Wear protective anti-acid clothing, gloves, boots, glasses.
Drainage disposal is forbidden.
Use in a ventilated room.
When in contact with other metals (carbon steels), Fluidox ECR decomposes and releases red nitrous fumes which should not be inhaled.

HOW TO USE ?

Fluidox ECR is ready to use

Spray under low pressure (2 to 3 bars) with acid resistant equipments (pumps, Laser G8.) polyethylene or polypropylene or PVC made.

Spray a thin and regular layer on the surface to be pickled.

Rinse after one or two hours with high pressure water.

Neutralize the effluents with **NEUTRIL C** before disposal.

Avoid the contact with other metals (dangerous nitrous fumes).

Do not work in confined spaces; do ventilate the area.

ASK FOR AND CONSULT THE SAFETY DATA SHEET